

WACKER

CREATING TOMORROW'S SOLUTIONS

ELASTOSIL®

PRODUCT OVERVIEW

INDUSTRIAL COATING OR SEALING APPLICATIONS

Flowable RTV silicone grades (self-adhesive)

Main characteristics Brand/ Product	Product type / curing system	Shrink- free curing	By-product of curing	Additional features	Food compli- ance	Viscosity [mPa·s]	Potlife or skin forming time	Hardness [Shore A]	Tensile strength [MPa]	Elongation at break [%]	Tear strength [N/mm]	Density, cured [g/cm ³]	Recommended max. service temperature [°C]	Aspect / color	Main characteristics Brand/ Product
Self-adhesive after curing at room temperature														Self-adhesive after curing at room temperature	
General purpose														General purpose	
ELASTOSIL® A 07	RTV-1 / condensation cure		Amine	Solvent based		8,000	3 min	20	1.5	300	4.0	1.02	200	Translucent	ELASTOSIL® A 07
ELASTOSIL® E 41	RTV-1 / condensation cure		Acetic acid	Solvent based		65,000	15 min	40	6.0	350	11.5	1.12	180	Translucent	ELASTOSIL® E 41
ELASTOSIL® E 50 N	RTV-1 / condensation cure		Acetic acid	Titanium catalyzed	X	50,000	10 min	35	1.5	150	5.0	1.07	180	Transparent	ELASTOSIL® E 50 N
ELASTOSIL® E 303	RTV-1 / condensation cure		Acetic acid	Solvent based		500	5 min	30	5.0	400		0.90	180	Translucent	ELASTOSIL® E 303
ELASTOSIL® N 2010	RTV-1 / condensation cure		Alcohol			15,000	20 min	25	1.0	200		1.01	180	Translucent	ELASTOSIL® N 2010
ELASTOSIL® RT 745 T	RTV-2 / platinum cure (A/B 1:1)	X				1,000	4 h	5	1.0	100		0.97	160	Brownish	ELASTOSIL® RT 745 T
Heat resistance														Heat resistance	
ELASTOSIL® A 234	RTV-1 / condensation cure		Amine			35,000	15 min	36	2.5	200	3.7	1.19	230	White	ELASTOSIL® A 234
ELASTOSIL® A 316	RTV-1 / condensation cure		Amine	Solvent based		500	5 min	15	0.8	200		1.02	180	Translucent	ELASTOSIL® A 316
ELASTOSIL® A 59	RTV-1 / condensation cure		Amine	Oil resistant		60,000	45 min	20	1.2	300	3.0	1.43	210	Gray	ELASTOSIL® A 59
ELASTOSIL® E 10	RTV-1 / condensation cure		Acetic acid			8,000	10 min	25	2.5	300	7.3	1.10	250	Red	ELASTOSIL® E 10
ELASTOSIL® E 60 N	RTV-1 / condensation cure		Acetic acid	Titanium catalyzed	X	80,000	5 min	35	2.5	250		1.07	230	Black / gray / red	ELASTOSIL® E 60 N
ELASTOSIL® RT 772	RTV-2 / condensation cure (Base + Catalyst 10:1)*		Alcohol			35,000	5 min / 10 min *	35	2.2	200		1.26	230	Black	ELASTOSIL® RT 772
Flame Retardant														Flame Retardant	
ELASTOSIL® N 2034	RTV-1 / condensation cure		Alcohol			25,000	20 min	35	2.0	200		1.16	180	Black	ELASTOSIL® N 2034
ELASTOSIL® N 2076	RTV-1 / condensation cure		Alcohol	EN 45545 compliant		150,000	15 min	36	1.6	150		1.30	180	Anthracite	ELASTOSIL® N 2076
Self-adhesive after curing at elevated temperature														Self-adhesive after curing at elevated temperature	
General purpose														General purpose	
ELASTOSIL® RT 720	RTV-2 / platinum cure (A/B 10:1)	X				30,000	6 h	35	5.0	200		1.13	180	Gray	ELASTOSIL® RT 720
Heat resistance														Heat resistance	
ELASTOSIL® RT 705	1-component heat-curing / platinum cure	X				72,500	6 months	42	3.5	200	3.5	1.24	230	Black	ELASTOSIL® RT 705
ELASTOSIL® RT 706	1-component heat-curing / platinum cure	X				15,000	6 months	30	2.5	200		1.23	210	Red	ELASTOSIL® RT 706
ELASTOSIL® RT 707 W	1-component heat-curing / platinum cure	X				60,000	6 months	42	3.3	270		1.18	230	White	ELASTOSIL® RT 707 W
ELASTOSIL® RT 708	1-component heat-curing / platinum cure	X		UV fluorescent		75,000	6 months	42	3.5	300		1.36	230	Dark gray	ELASTOSIL® RT 708

* base component to be combined with WACKER® Catalyst T 77 or WACKER® Catalyst T 77 PLUS (please see the corresponding technical data sheet for details)

Note: these figures are intended as a guide and should not be used in preparing specifications.

WACKER

Wacker Chemie AG
Gisela-Stein-Straße 1
81671 Munich, Germany
www.wacker.com/contact

www.wacker.com

Follow us on:



7461_C_en/11_24 replaces 7461_C_e/04_24

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.